



# Aniègre

## BOTANICAL NAMES

*Aningeria robusta*.

It belongs to the Sapotaceae family.

## TRADE NAMES

Anegrè, Aningeria, Aniègre, Mukali, Noce Tanganika.

## GROWING AREAS

African equatorial belt from Ivory Coast to Kenya.

## TECHNOLOGICAL FEATURES

Undifferentiated sapwood and heartwood. It is reddish-brown with straight grain and fine texture. It is heavy, moderately hard and not very elastic. It is not very hard against fungi and insects. It is attacked by *Lyctus*. It must be treated with effective preservatives before use.

## DRYING METHOD

It happens easily and without risk, sometimes there can be splits due to internal tension.

## SPECIFIC WEIGHT

Seasoned on open-air, it has a specific weight that changes from 550 to 600 Kg/m<sup>3</sup>.

## MAIN USES AND WORKING

Used in the furniture industry, stained resembles walnut and can be used in its stead but has nothing to do with it. Used extensively for hardwood floors and doors.

**ZANUSO**legno

"Details make perfection  
and perfection is not a  
detail."